



Advanced Materials Technical Datasheet



Araldite[®] 2014 Structural Adhesive

Product Description

Araldite[®] 2014 structural adhesive is a two component, room temperature curing, thixotropic paste adhesive of high strength with good environmental and excellent chemical resistance. Used for bonding of metals, electronic components, GRP structures and many other items where a higher than normal temperature or more aggressive environment is to be encountered in service. The low out gassing makes this product suitable for specialist electronic telecommunication and aerospace applications.

Features

- Grey paste
- High temperature and chemical resistance
- Low shrinkage
- Very resistant to water and a variety of chemicals
- Gap filling, non-sagging up to 0.197 in (5 mm) thickness

Typical Properties*

Property	Araldite [®] 2014 A	Araldite [®] 2014 B	Mixed System
Appearance	Beige paste	Grey paste	Grey paste
Density, g/cm ³	~1.6	~1.6	~1.6
Viscosity at 25°C, cP	~100,000	Thixotropic	Thixotropic
Pot life at 25°C, 100 g, min	--	--	~40

*Properties are based on Huntsman test methods. Copies are available upon request

Processing

Mix Ratio

Product	Parts by weight	Parts by volume
Araldite [®] 2014 A	100	100
Araldite [®] 2014 B	50	50

Pretreatment

The strength and durability of a bonded joint are dependent on proper treatment of the surfaces to be bonded. At the very least, joint surfaces should be cleaned with a good degreasing agent such as acetone, isopropanol (for plastics) or other proprietary degreasing agents in order to remove all traces of oil, grease and dirt. Low-grade alcohol, gasoline, or paint thinners should never be used. The strongest and most durable joints are obtained by either mechanically abrading or chemically etching (“pickling”) the degreased surfaces. Abrading should be followed by a second degreasing treatment.

Araldite® 2014 structural adhesive is available in cartridges incorporating mixers and can be applied as ready to use adhesive with the aid of the tool recommended by Huntsman Advanced Materials.

Application of adhesive

The resin/hardener mix may be applied manually or robotically to the pretreated and dry joint surfaces. Huntsman's technical support group can assist the user in the selection of a suitable application method as well as suggest a variety of reputable companies that manufacture and service adhesive dispensing equipment. A layer of adhesive 0.002 to 0.004 in (0.05 to 0.10 mm) thick will normally impart the greatest lap shear strength to the joint. Huntsman stresses that proper adhesive joint design is also critical for a durable bond. The joint components should be assembled and secured in a fixed position as soon as the adhesive has been applied. For more detailed explanations regarding surface preparation and pretreatment, adhesive joint design, and the dual syringe dispensing system, visit www.araldite2000plus.com.

Equipment Maintenance

All tools should be cleaned with hot water and soap before adhesives residues have had time to cure. The removal of cured residues is a difficult and time-consuming operation. If solvents such as acetone are used for cleaning, operatives should take the appropriate precautions and, in addition, avoid skin and eye contact.

Cure times to reach minimum shear strength

Temperature, °F	50	59	73	104	140	212
Cure time to reach LSS* > 145 psi (1 MPa), hours minutes	14 -	8 -	3 -	- 60	- 15	- 3
Cure time to reach LSS > 1450 psi (10 MPa), hours minutes	20 -	11 -	5 -	- 80	- 20	- 4

*LSS = Lap shear strength

Typical Physical Properties

Unless otherwise stated, the data were determined with typical production batches using standard test methods. They are typical values only, and do not constitute a product specification.

Unless a different specification is given, the figures below were all determined by testing standard specimens made by lap-jointing 4.5 x 1 x 0.063 in (114 x 25 x 1.6 mm) strips of aluminum alloy. The joint area was 0.5 x 1 in (12.5 x 25 mm) in each case.

Samples were cured at 104°F (40°C) for 16 hours and tested at 23°C, unless otherwise noted.

Property	Value			Test Method
Average lap shear strength, metal-metal joints, sand blasting pre-treatment, psi				ISO 4587
Aluminum	2,762			
Steel 37/11	2,487			
Stainless steel V4A	3,149			
Galvanized steel	1,321			
Copper	2,358			
Brass	2,347			
Average lap shear strength, plastic-plastic joints, lightly abrade and alcohol degrease pre-treatment, psi				ISO 4587
GRP	1,247			
CFRP	1,944			
SMC	1,204			
ABS	450			
PVC	421			
PMMA	218			
Polycarbonate	435			
Polyamides	363			
Lap shear strength, after immersion in 23°C media, psi	30 days	60 days	90 days	ISO 4587
As-made value	--	--	2,764	
IMS	222	513	2,799	
Gasoline	560	1,213	3,191	
Ethyl acetate	2,321	2,611	3,336	
Acetic acid, 10%	793	1,691	2321	
Xylene	1,492	1,971	2,741	
Lubricating oil	2,176	2,031	2,357	
Paraffin	2,321	3,336	2,756	
Water at 73°F	--	--	2,450	
Water at 140°F	3,549	2,889	2,812	
Water at 194°F	1,015	2,715	2,094	


Lap shear strength, exposure to tropical weather,* psi		
As-made value	2,708	DIN 50015
30 days	3,078	
60 days	3,191	
90 days	2,901	
Lap shear strength, heat aging at 158°F, psi		
As-made value	2,712	--
30 days	2,843	
60 days	2,654	
90 days	3,017	
Roller peel test, pli (N/mm)	17 (3.0)	ISO 4578
Glass transition temperature (DSC), T _g , °F (°C) Cure: 24 hour at 73°F + 1 hour at 176°F	185 (85)	Huntsman
E-modulus at 23°C, psi (GPa)	580,151 (4)	ISO R527
Flexural strength, psi (MPa)	8,847 (61)	ISO 178
Flexural modulus [†] , psi (MPa)	631,475 (4355)	ISO 178
Tensile strength, psi (MPa)	3,773 (26)	
Elongation at tensile break, %	0.7	
Shear modulus, psi (MPa)		DIN 53445
122°F (50°C)	174,045 (1200)	
167°F (75°C)	58,015 (400)	
212°F (100°C)	26,107 (180)	
257°F (125°C)	2,901 (20)	

*40/92, DIN 50015; typical average values; test at 23°C.

† Cure 1 day / 73°F (23°C) + 30 mins / 176°F (80°C); tested at 73°F (23°C)

Figure 1. Lap shear strength versus temperature (ISO 4587) (typical average values)

Cure: (a) = 7 days at 73°F (23°C); (b) = 24 hours at 73°F (23°C) + 30 min / 176°F (80°C)



Storage

Araldite® 2014 Adhesive should be stored in a dry place, in the original sealed containers, at temperatures between 2°C and 40°C (36°F and 104°F). Under these storage conditions, the product has a shelf life of **3 years** (from date of manufacture). The product should not be exposed to direct sunlight.

If stored below 60°F, the adhesive should be brought to 60°F - 77°F and conditioned at this temperature for some time prior to use.

Precautionary Statement

Huntsman Advanced Materials Americas LLC maintains up-to-date Safety Data Sheets (SDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

First Aid!

Refer to SDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN

FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

Important Legal Notice

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

Araldite is a registered trademark of Huntsman LLC or an affiliate thereof in one or more, but not all countries.

© 2015 Huntsman Advanced Materials Inc.



1-800-375-0605
Option 8 for 24/7 Service



6550 Oley Speaks Way
Canal Winchester, OH 43110



www.RudolphBros.Com
RBCsupport@RudBro.Com