



Technical Data Sheet Titan 7243

www.cyberbond1.com
"The Power of Adhesive Information"™



Authorized Distributor
1-800-375-0605
www.rudolphbros.com

Product Description

Titan 7243 is a single component anaerobic threadlocking adhesive, which is thixotropic and develops medium strength. The product cures between close fitting metal parts where there is an absence of air.

Typical Applications

Prevents loosening of threaded fasteners. Suitable for applications where disassembly with hand tools is required for servicing. Bonds well to oily, or otherwise contaminated metal surfaces.

Physical Properties

Monomer (Liquid)

Base Compound	Dimethacrylate Ester
Appearance	Blue liquid
Viscosity (cP @ 68°F)	2250 cP
Specific Gravity (g/cc)	1.1
Gap Fill	.007"
Corrosivity	None
Flash Point (TCC)	>200°F
Toxicity	Low
Shelf Life @40°F	1 year unopened

Military Specifications

Mil-S-46163A
Type II, Grade N

Curing Properties

The rate of cure will depend on environmental conditions and the substrates used.

Setting Time (68°F, 65% R.H.)

Substrate	Set time/Full Cure
Steel	15 min/24 hrs
Brass	15 min/24 hrs
Zn Dichromate	20 min/24 hrs
Stainless Steel	20 min/24 hrs

Curing Performance

The gap of the bond line will affect set speed. Smaller gaps tend to increase the speed. Activators can be applied to improve set speed but may also impair overall adhesive performance.

Polymer (Cured)

Locking Strength	Medium
Appearance	Blue Solid
Service Temperature Range	-75°F to 300°F
Full Cure Time	24 Hours
Sheer Strength (steel nuts and bolts)	1200 psi


Performance of Cured Materials

Bond strength after 24 hours at 20° to 25°C on steel nuts and bolts.

	Avg. Value	Range
Breakaway Torque	155 in. lbs.	140-175 in. lbs.
Prevailing Torque	70 in. lbs.	35-100 in. lbs.

Temperature Resistance

% Retained strength when tested at temperature



Technical Data Sheet

Titan 7243

Chemical Resistance

Sheer strength on steel after 500 hours

Solvent	% Strength Retained
Motor Oil	100
Unleaded Gasoline	100
Trichloroethane	100
Brake Fluid	100
Ethanol	100
Acetone	100
Water/Glycol Mix	80

General Instructions

Surfaces to be bonded should be clean and dry and free of grease.

Product should be applied in enough quantity to fill all engaged threads. The product performs best in thin bond gaps. Very large gaps may create gaps which will affect the cure speed and overall strength. Good contact is essential. An adequate bond develops in 15 to 45 minutes and maximum strength is attained in 24 hours.

This product is not recommended for use in pure oxygen environments and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

This product is not designed for plastics, particularly thermoplastics where stress cracking of the plastic could result. It is recommended to confirm compatibility of the product with all substrates prior to use.

Storage

Products should be stored unopened in a cool, dry place out of direct sunlight. Products can be refrigerated for improved shelf life but should be brought back to room temperature before use.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS)

NOTE

The data contained herein are furnished for information only and are believed to be reliable. Cyberbond L.L.C. cannot assume responsibility for the results obtained by others over whose method Cyberbond L.L.C. does not control. It is the user's responsibility to determine suitability for the product or of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Cyberbond L.L.C. specifically disclaims all warranties of merchantability or fitness for a particular purpose arising from sale or use of Cyberbond L.L.C. products. Cyberbond L.L.C. specifically disclaims any liability for consequential or incidental damages of any kind, including loss of profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Cyberbond L.L.C. patents which may cover such processes or compositions. We recommend that each prospective user test the proposed application to determine its suitability for the purpose intended prior to incorporating any product or application in its manufacturing process using the data as a guide.