

Cyberbond

**Apollo
2077**

TECHNICAL DATA SHEET

The Power of Adhesive Information
cyberbond
TM

Apollo 2077 is a single component, medium viscosity cyanoacrylate adhesive. It is suitable for general-purpose bonding, particularly providing excellent strength and speed on all rubber compounds. Apollo 2077 is certified to ISO 10993-5, 10993-10 and 10993-11 for biocompatibility, making it suitable for use in medical applications.

Physical Properties - Monomer (Uncured)

Base Compound	Ethyl
Appearance	Clear
Viscosity	800 +/- 150 cPs
Specific Gravity	1.06 g/cc
Flash Point	85°C/ 185°F
Shelf Life	12 mo
Storage Condition	15.5°C/ 60°F
RoHS-Compliant	yes


Physical Properties - Polymer (Cured)

Full Cure Time	24 hours
Appearance	Clear
Service Temp Range	-55 to 95 °C (-67 to 203 °F)

Specifications and Approvals

10993-5, 10993-10, 10993-11
Mil-A-46050C, Type II Class III, A-A-3097, Type II Class 3


Hot Strength (%RT strength, tested at temperature)



Setting Time

Steel	35	seconds
ABS	6	seconds
EPDM	4	seconds

Time Until Full Cure (% of RT strength)



Performance of Cured Adhesive


Substrate	N/mm ²		PSI	
Steel	13.8	to 18.8	2000	to 2730
Rubber*	5.1	to 15.2	735	to 2200
AL	3.1	to 3.5	450	to 510
PC**	22.3	to 24.9	3240	to 3605
PVC**	18.3	to 26.7	2660	to 3875
ABS**	12.0	to 18.3	1740	to 2660

*Rubber figures given are typical. Your results may vary by specific rubber type.


**Tested to ASTM 4501

***n/r = not recommended

Performance Range, by Substrate



Heat Aging (aged at temp indicated and tested @ 22°C)



Solvent Resistance

Solvent	Example	Resistance
Alcohol	Ethanol, Methanol	+++
Ester (aromatic)	Ethylacetate	---
Ketone (aromatic)	Acetone, Benzophenone	---
Aliphatic hydrocarbon (alkanes)	Petrol, Heptanes, Hexane	++-
Aromatic hydrocarbons	Benzyl, Toluol, Xylol	++-
Halogenated hydrocarbons	Methylenchloride, Chloroform, Chlorobenzol	---
Weak aqueous acid	Nitrite, muriatic acid, sulphuric acid, phosphoric acid	+++ (--- if concentrated)
Weak aqueous base	sodium hydroxide solution, caustic potash	+++ (--- if concentrated)

General Instructions

Surfaces to be bonded should be clean and dry. Dispense a drop or drops to one surface only. Apply only enough to leave a thin film layer after compression. Press parts together and hold firmly for a few seconds. Good contact is essential. An adequate bond develops in less than one minute and maximum strength is attained in 24 hours. Wipe off excess adhesive from the top of the container and recap. Apollo products if left uncapped may deteriorate by contamination from moisture in the air. Because Apollo products cure by polymerization, whitening may appear on the surface of the container or the bonded materials. This will not affect adhesive performance.

Curing Performance

Ambient surface moisture initiates the curing process. Handling strength is reached in a short time, and will vary based on environmental conditions, bond line gap, and other factors. Product will continue to cure for at least 24 hours before full strength and solvent resistance is developed.

Storage

Products should be stored unopened in a cool, dry place out of direct sunlight. Products should be kept at room temperature away from direct light. Protect from extreme heat or cold, do not refrigerate.

Updated

3/12/2013

Note

The data contained herein are furnished for information only and are believed to be reliable. Cyberbond cannot assume responsibility for the results obtained by others over whose method Cyberbond does not control. It is the user's responsibility to determine suitability for the product or of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Cyberbond specifically disclaims all warranties of merchantability or fitness for a particular purpose arising from sale or use of Cyberbond products. Cyberbond specifically disclaims any liability for consequential or incidental damages of any kind, including loss of profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Cyberbond patents which may cover such processes or compositions. We recommend that each prospective user test the proposed application to determine its suitability for the purpose intended prior to incorporating any product or application in its manufacturing process using the data as a guide.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS)



Authorized Distributor

1-800-375-0605

www.rudolphbros.com

