



Authorized Distributor

1-800-375-0605

www.rudolphbros.com



Product Datasheet General Casting System

Physical Properties of BC 8500 series

Property	BC8595	BC8590	BC8585	BC8575	BC8565
Shore A Hardness, (± 3)	95	90	85	75	68
Ultimate Tensile, PSI	1940	1980	1810	1330	1200
Elongation, %	160	360	500	500	530
Tear, Die C, PLI	370	336	240	187	170
Gel Time, Minutes	7 - 10	7 - 10	7 - 10	7 - 10	7 - 10
Mold Temperature	160° F (71° C)	160° F (71° C)			
Post-cure Time @ 150° F Hours	16	16	16	16	16
Post-cure Time @ 190° F Hours	8	8	8	8	8
Mix Ratio by Weight (Polyol:Prepolymer)	100:72	100:60	100:47	100:39	100:35
Color	Black or Natural (white)	Black or Natural (white)	Black or Natural (white)	Black or Natural (translucent white)	Black or Natural (translucent white)

Safety: Read and understand MSDS's before use. Use only in well ventilated areas. Avoid contact with skin. Wear chemical resistant gloves and proper safety equipment. If swallowed, call physician immediately. For eye contact, flush with water for 15 minutes and get medical attention.

The conditions for your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by BCC Products. All information is given without warranty or guarantee. It is expressly understood and agreed that customer assumes and hereby expressly releases BCC Products from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind BCC Products. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.