



**RUDOLPH BROS. & COMPANY**  
6550 OLEY SPEAKS WAY  
CANAL WINCHESTER, OHIO 43110  
PHONE: 614-833-0707  
FAX 800-600-9508  
www.rudolphbros.com

## **HIGH STRENGTH 1-PART INDUSTRIAL/CONSTRUCTION GRADE SILICONE SEALANT**

RB-100 is a one component room temperature vulcanizing RTV acetoxy cure silicone sealant and adhesive that has been chemically formulated for high strength adhesion. When fully cured, this unique VOC compliant formula offers UV stability and excellent adhesion to form waterproof and airtight bonds to metal, steel, tile, fiberglass, ceramic, glass, aluminum, painted surfaces, wood, plywood, marble, plus many other common substrates. This product is specifically formulated to offer all weather performance to meets today's Green Building Standards.

### **Features and Benefits**

High Strength  
Excellent Weatherability  
UV Stable  
Non-Yellowing

VOC Compliant  
Non-Flammable  
Waterproof  
Excellent Adhesion  
Non-Shrinking

### **Construction and Industrial Applications**

Sealing & Glazing  
HVAC/R  
Plumbing  
Roofing  
Kitchen And Bath  
Countertops

Sanitary Seals  
Precast Concrete  
Transportation Seals  
Marine Cabins  
Appliance Trim  
Interior/Exterior  
Above Grade

**MEETS SPECIFICATIONS:** ASTM C920 Type S, NS, Class 25; TT-S-00230C, TT-S-01543A, MIL-A-46106A, FDA CFR 177.2600, USDA Approved, NSF 51, UL Recognized Component.

**AVAILABLE COLORS:** Clear, White, Black, Aluminum, Almond, Bronze, Gray, Trans White (custom colors available upon request)

Physical Properties		Test Method
Cure System	Acetoxy	
Movement Capability, %	±25%	ASTM C-719
Modulus	Medium	ASTM D-412
Physical Properties (Cured)	Rubber	
Specific Gravity	1.04	
Extrusion Rate, g/min	370	ASTM C-1183
- 1/8" orifice @ 50 psi		Modified
Temperature Range	-62° F to 350° F	
Intermittent Temperature Range	400° F	
Accelerated Weathering (10,000 hrs.)	No Change	QUV Weatherometer
Skin Over Time (min)	10*	MNA Method
Tack Over Time (min)	17*	ASTM C-679
Cure Rate	1/8" per 24hrs*	MNA Method
Tensile Strength (psi)	310	ASTM D-412
Elongation %	500	ASTM D-412
Durometer Shore A	26	ASTM C-661
Dielectric Strength kv/mm (v/mil)	20 (500)	
Dielectric Constant at 100 Hz	2.7 @ 60	
Shelf Life (months)	24	
Volatile Organic Content	30 gr./liter	

\*All properties derived from lab conditions (77 ° F at 50% relative humidity)

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

RUDOLPH BROS. & COMPANY  
6550 OLEY SPEAKS WAY  
CANAL WINCHESTER, OHIO 43110

PHONE: 614-833-0707  
FAX 800-600-9508  
www.rudolphbros.com



**Authorized Distributor**

1-800-375-0605  
www.rudolphbros.com