

LOCTITE[®] Frekote WOLO[™]

Known as Frekote WOLO
January 2015

PRODUCT DESCRIPTION

LOCTITE[®] Frekote WOLO[™] provides the following product characteristics:

Technology	Mold Release
Appearance	Clear, colorless ^{LMS}
Chemical Type	Solvent Based Polymer
Odor	Hydrocarbon
Cure	Room temperature cure
Cured Thermal Stability	≤400 °C
Application	Release Coatings
Application Temperature	13 to 41 °C
Specific Benefit	<ul style="list-style-type: none">• High gloss finish• Easy application• Fast curing• Multiple releases• Minimal mold build-up

LOCTITE[®] Frekote WOLO[™] is a unique, low VOC polymer release agent that cures quickly and provides multiple release of all polyester resins. Applications and use of a release agent has never been easier, simply wipe on and leave on to produce a high gloss finish with no need to polish.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C

0.71 to 0.73^{LMS}

Flash Point - See SDS

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Mold Preparation

Cleaning:

Mold surfaces must be thoroughly cleaned and dried. All traces of prior release must be removed. This may be accomplished by using Frekote[®] PMC or other suitable cleaner. Frekote[®] 915WB[™] or light abrasives can be used for heavy build-up.

Sealing New/Repaired Molds:

Fully cured unused molds should be sealed before use. This can be accomplished by applying 4 additional coats of LOCTITE[®] Frekote WOLO[™]. Fresh or "production line" repairs, new fiberglass and epoxy molds should be cured per manufacturer's instructions, usually a minimum of 2 -3 weeks

at 22°C before starting full-scale production. Occasionally, green or freshly repaired molds are rushed into service prior to complete cure causing an increased amount of free styrene on the mold surface. These areas of the mold surface would be considered extremely green due to the short cure time and will require the extra styrene sealing capability of Frekote[®] Mold Sealer. Sealing may be accomplished by wiping 2-3 coats of Frekote[®] Mold Sealer onto the repaired area(s). Allow full cure of the appropriate Frekote[®] mold sealer before you apply the first coat of LOCTITE[®] Frekote WOLO[™] as outlined in the directions of use.

Directions for use:

1. Apply LOCTITE[®] Frekote WOLO[™] with a clean, lint free, cotton wiping cloth. Wet the cloth with LOCTITE[®] Frekote WOLO[™] until it is damp but not dripping.
2. Wipe a smooth, wet film over the entire mold surface. For larger molds, apply LOCTITE[®] Frekote WOLO[™] to the surface one section at a time starting at one end and working towards the other. Continue to work the material into the mold by lightly wiping the wet film (10-30 seconds) until a thin and uniform coating is obtained, and then allow the product to evaporate.
3. Allow a minimum of 5 minutes before applying next coat. Apply a minimum of four coats in this manner. Dampen cloth lightly as needed.
4. Allow the final coat to cure for 15 minutes at 20°C.
5. **NOTE:** If the cloth dries out during your coating process, use a fresh clean cloth to apply the next coat. This prevents resin accumulation on the cloth from being deposited on the mold surface. If streaking occurs, replace the cloth with a clean dry one and/or make sure that the cloth is just damp and not soaking wet. Avoid over-application, as this will cause streaking on the tooling surface. Streaks or wipe lines can be removed easily by wiping the mold surface lightly with a dry cloth. Product is moisture sensitive, keep container tightly closed when not in use.
6. **NOTE:** For maximum number of releases, apply a touch up coat after the first 2-3 parts are released as a break in period after the initial application. On deep or high wear areas, apply an extra 1-2 coats of LOCTITE[®] Frekote WOLO[™]. This will help increase the slip even further in these high drag areas.

Mold Touch up

Abrasion will gradually cause wear and parts will begin to adhere to the mold surface if a continuous release film is not maintained. It's best to always touch-up the mold at the first

sign of diminished release, before release becomes difficult. Simply touch-up the entire mold or apply spot touch-ups to high wear areas following steps 1-3 under directions for use. Only 1 coat is usually required for touch-up. Typically, 15 minutes cure time is required prior to resumption of molding.

Loctite Material Specification^{LMS}

LMS dated January 24, 2007. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

The product is classified as flammable and must be stored in an appropriate manner in compliance with relevant regulations. Do not store near oxidizing agents or combustible materials. Store product in the unopened container in a dry location. Storage information may also be indicated on the product container labelling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1