



Technical Process Bulletin



BONDERITE M-CR 1201 AERO CHROMATE COATING (KNOWN AS ALODINE 1201)

Issued: 12/17/2018

1. Introduction:

BONDERITE M-CR 1201 AERO (known as ALODINE 1201) is a nonflammable, chromic acid based, coating chemical that will produce a chrome conversion coating on aluminum and its alloys.

BONDERITE M-CR 1201 AERO (known as ALODINE 1201) is approved to MIL-DTL-81706 for brush application only. BONDERITE M-CR 1201 AERO (known as ALODINE 1201) is used as received for MIL-DTL-5541 work. Adjustments and titrations are not needed or required. Used solutions should be discarded.

The coating formed by BONDERITE M-CR 1201 AERO (known as ALODINE 1201) is gold to tan in color and it becomes a part of the aluminum surface. This chrome conversion coating offers the best affordable substrate for both paint adhesion and corrosion resistance.

2. Operating Summary:

Brush Application:

Apply to a chemically cleaned surface using the solution undiluted from the container.

Immersion Application:

For each 100 parts of bath, mix 33 parts of BONDERITE M-CR 1201 AERO (known as ALODINE 1201) and 67 parts of water.

Operation and Control:

Time	2 to 5 minutes
Temperature	Ambient to 100° Fahrenheit

3. The Process:

The process to prepare metal for painting normally consists of the following steps:

- A. Cleaning BONDERITE C-IC 33 AERO (known as ALUMIPREP® 33)
- B. Water rinsing
- C. Apply BONDERITE M-CR 1201 AERO (known as ALODINE 1201)
- D. Water rinsing
- F. Drying

The work, after processing and drying, is ready to be painted.

Revision History
8.20.18
12.17.18





BONDERITE M-CR 1201 AERO CHROMATE COATING (KNOWN AS ALODINE 1201)

4. Materials:

BONDERITE M-CR 1201 AERO (known as ALODINE 1201)
BONDERITE C-IC 33 AERO (Known as ALUMIPREP 33)

5. Equipment:

Acid resisting (rubber, stainless steel or plastic) buckets, troughs or other suitable containers should be used to hold the BONDERITE M-CR 1201 AERO (known as ALODINE 1201) or diluted BONDERITE M-CR 1201 AERO (known as ALODINE 1201) solution. Ordinary steel pails may be used, but only for a short time. Galvanized containers should not be used. If production conditions warrant, troughs may be installed to collect the BONDERITE M-CR 1201 AERO (known as ALODINE 1201) coating chemical run-off for reuse.

Long handled, window type brushes, clean cloths or synthetic sponges may be used to brush on the BONDERITE M-CR 1201 AERO (known as ALODINE 1201).

6. Surface Preparation:

Cleaning:

BONDERITE C-IC 33 AERO (known as ALUMIPREP 33) is recommended for cleaning. BONDERITE C-IC 33 AERO (known as ALUMIPREP 33) is a nonflammable, phosphoric acid based cleaner which produces a chemically clean and corrosion free aluminum surface. Instructions for use of BONDERITE C-IC 33 AERO (known as ALUMIPREP 33) are found in that Technical Process Bulletin.

Water Rinsing:

After cleaning, the metal must be thoroughly rinsed with water. Inadequate rinsing may contaminate a BONDERITE M-CR 1201 AERO (known as ALODINE 1201) immersion bath or result in a surface condition which may cause corrosion of the finished part.

7. Apply BONDERITE M-CR 1201 AERO (known as ALODINE 1201):

Buildup:

For brush application, BONDERITE M-CR 1201 AERO (known as ALODINE 1201) is applied to a chemically cleaned surface using the solution undiluted.

For immersion application, BONDERITE M-CR 1201 AERO (known as ALODINE 1201) is diluted by mixing 33 parts of BONDERITE M-CR 1201 AERO (known as ALODINE 1201) and 67 parts of water for each 100 parts of bath volume required.

NOTE: Operators should be equipped with rubber gloves, aprons and goggles to avoid contact with the solution. Adequate ventilation should be provided.

Operation:

Time: 2 minutes to 5 minutes.
Temperature: Room temperature to 100° Fahrenheit.





BONDERITE M-CR 1201 AERO CHROMATE COATING (KNOWN AS ALODINE 1201)

BONDERITE M-CR 1201 AERO (known as ALODINE 1201) coating chemical should not be allowed to dry on the metal surface. With brush application the surface should be rewet with fresh BONDERITE M-CR 1201 AERO (known as ALODINE 1201) several times during the treatment time. If drying does occur, rewet with BONDERITE M-CR 1201 AERO (known as ALODINE 1201) coating chemical prior to water rinsing.

Selecting the size of the area to be treated at one time depends on the method of application, condition of the metal surface, method in which the surface was cleaned, temperature and part configuration.

Colors of the coating produced by BONDERITE M-CR 1201 AERO (known as ALODINE 1201) will vary from a light gold to a dark tan. Variations in color result from different alloys, metal hardness, metal age, method of cleaning, etc.

Powdering of a chrome conversion coating can result from poor cleaning, drying, over reacting, or for other reasons. Powder can affect paint adhesion. Gently wipe and remove the powder, without abrading the chemical coating, with a dry, clean rag after the work has dried. Caution should be taken not to redeposit oils, lint or other soils back on the aluminum surface.

8. After Treatment:

Water Rinsing:

A thorough rinse with clean water is necessary to remove residual BONDERITE M-CR 1201 AERO (known as ALODINE 1201) coating chemical salts from the metal surface. Blistering and corrosion problems under paint are often the results of poor rinsing. Chemical salts trapped under a paint film will eventually result in blistering or corrosion problems.

Drying:

As an aid to drying, heating the treated part, blowing off with clean, dry, filtered, forced air or gently wiping with a dry, clean rag will lessen the time required. Do not allow the aluminum metal temperature to exceed 140 Fahrenheit.

Paint soon after the work is dry in order to prevent soils or oxidation from recontaminating the prepared metal surface.

9. Storage Requirements:

BONDERITE M-CR 1201 AERO (known as ALODINE 1201) coating chemical will freeze at 32° Fahrenheit. It is recommended that the product be stored where freezing will not occur. However, should it freeze, simply thaw it in a warm place and stir it prior to use.

10. Waste Disposal Information:

Applicable regulations concerning disposal and discharge of chemicals should be consulted and followed.

Disposal information for the chemical products used in this process is given on the Material Safety Data Sheet for each product.

The processing bath is acidic and contains hexavalent chromium. Waste treatment and neutralization may be required prior to discharge to sewer.





BONDERITE M-CR 1201 AERO CHROMATE COATING (KNOWN AS ALODINE 1201)

11. Precaution:

Consult the appropriate Material Safety Data Sheets for safety and handling guidelines for the products listed in this bulletin.

NOTICE:

The above information and recommendations concerning this product are based upon our laboratory tests and field use experience. However, since conditions of actual use are beyond our control, any recommendations or suggestions are made without warranty, express or implied. Manufacturer's and seller's sole obligation shall be to replace that portion of the product shown to be defective. Neither shall be liable for any loss, damage, or injury, direct or consequential, arising out of the use of this product.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.



**RUDOLPH
BROS. & CO**



1-800-375-0605
Option 8 for 24/7 Service



www.rudolphbros.com
rbcsupport@ruidbro.com

