

TECHNICAL INFORMATION

WS-8030 Class B

Light Weight, High Temperature Resistant Fuel Tank and Fuselage Sealant

PRODUCT DESCRIPTION

WS-8030 Class B is a two component light weight manganese dioxide cured polysulfide sealant designed to meet the requirements of AMS 3281 fuel tank specifications. It has outstanding adhesion to the common aerospace substrates as well as excellent sealing characteristics at temperatures ranging from -65°F (54°C) to 250°F (121°C), including intermittent exposure up to 360°F (182°C).

WS-8030 Class B exhibits excellent elastomeric properties and retention after prolonged exposure to jet fuel and aviation gasoline. The uncured product is a low sag thixotropic paste suitable for application by extrusion gun or spatula.

SPECIFICATIONS:

- AMS3281 Type 1 Qualified

APPLICATION PROPERTIES

Typical @77°F (25°C)	50%RH		
Slump, inches (mm)	<u>Initial</u>	<u>50min</u>	<u>90min</u>
B-1/2	0.1(2.54)		
B-2	0.1(2.54)	0.1(2.54)	0.1(2.54)

Base Viscosity Poise (pa-s), Brookfield #7 spindle @ 2 rpm	10,000 (1000)
--	---------------

Color

Part A	Black
Part B	White
Mixed	Dark gray

Mix Ratio

by weight	100 parts base (Part B) to 12 parts accelerator (Part A)
by volume	100 parts base to 7.8 parts accelerator

Cure Profile: (Standard Class B Sealant)

	<u>B-1/2</u>	<u>B-2</u>
Application Life (hrs)	½	2
Tack free time (hrs)	<10	<24
Cure time to 35 A Durometer (hrs)	<24	<48

Tooling Characteristics	Excellent
-------------------------	-----------

PERFORMANCE PROPERTIES

Typical 14 days @ 77°F (25°C), 50% RH
 (Tested per AMS-3281)

Color	Dark gray
Specific Gravity	1.25
Final hardness	51 shore A
Nonvolatile content	95%
Low temperature flexibility @ -65°F (-54°C)	No cracking or adhesion loss

Resistance to AMS2629 JRF Hydrocarbon 7 days 140° F exposure	
Weight loss	<6%
Thermal rupture resistance	Negligible deformation at 10 psi before and after fuel exposure in AMS2629 JRF.

Repairability	Excellent to itself and other sealant fresh or aged cure.
---------------	---

Excellent resistance to other fluids such as: water, alcohols, synthetic oils and petroleum based hydraulic fluids.

Fungus resistance	Non-nutrient
Sanding	Good

Peel Strength

pli, 100% cohesion, 7 days immersion @ 140°F (60°C) AMS2629 JRF and AMS2629 JRF/3% saltwater:

<u>Substrate</u>	<u>Conditioning</u>	<u>Adhesion*</u>
Mil-C-5541	JRF	28
(Alodine aluminum)	JRF/SW	28/30
AMS 2471	JRF	27
(Anodized aluminum)	JRF/SW	28/31
AMS 4901	JRF	28
(Titanium)	JRF/SW	28/30
AMS 5516	JRF	26
(Stainless steel)	JRF/SW	27/31
MIL-PRF-27725	JRF	29
(Fuel tank coating)	JRF/SW	27/30
Graphite epoxy	JRF	28
(AS 4/3501-6)	JRF/SW	28/31

Peel Strength (Cont.)

<u>Substrate</u>	<u>Conditioning</u>	<u>Adhesion*</u>
BMI	JRF	27
(IM7/5250-4)	JRF/SW	28/30
MIL-PRF-23377	DI water	29
(Primer coating)	SW	31

*Specification requirements- 20pli/100% cohesion

Tensile Strength and Elongation

Tensile Strength PSI (KPa) 300 (2055)
77°F (25°C) 50% RH
Elongation 300%

Tensile Strength Psi (Kpa) 270 (1860)
after 7 days exposure in
JRF at 140° F
Elongation 300%

Note: All values are typical and are not intended for specification use or for acceptance inspection criteria.

SURFACE PREPARATION

Surfaces must be cleaned with solvent. Use appropriate solvent and cloth in accordance with AMS 3281 specification.

PACKAGING

WS-8030 Class B is supplied in two part kit containers and cartridges for the purpose of facilitating mixing and application.

MIXING INSTRUCTIONS

Mix the two part kits and two part sealant cartridges as indicated on the container label. Do not forget to mix Part A and Part B of the two part kits to uniformity before blending them. Avoid leaving unmixed material around the side and bottom of the mixing container.

STORAGE LIFE

The shelf life of WS-8030 Class B is 9 months from the date of shipment when stored below 80°F (27°C) in the original unopened container. The storage life of premixed and frozen material is a minimum of 30 days at temperatures below -40°F (-40°C).

HEALTH PRECAUTIONS

proper care. Read the MSDS (Material Safety Data Sheet) for information on handling precautions, hazardous ingredients and first aid procedures. After use of his product, always wash your hands before eating or smoking. If you need an MSDS, this is always available on request. In case of overexposure, be sure to obtain medical care.

Keep away from children. This product is intended for industrial use only.

ADDITIONAL INFORMATION

Visit our web site at:

www.royaladhesives.com

Contact us at:

Royal Adhesives and Sealants, LLC
800 E Anaheim St
Wilmington, CA 90744
(800) 999-4583 Toll-free
(310) 830-9904 Phone
(310) 830-9908 Fax
Web: www.royaladhesives.com

NOTE

The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchases will be subject to a separate agreement, which will not incorporate this document.

Distributed by:

Rudolph Bros. & Co.

PO Box 425, Canal Winchester, OH 43110

Phone: 614-833-0707

Fax: 800-600-9508

e-mail: rbcsupport@rudbro.com

www.rudbro.com