•TRUSTED QUALITY SINCE 1921•

# **RUST-OLEUM**

INDUSTRIAL — CHOICE.—

# 1600 SYSTEM MULTI-PURPOSE ENAMELS

### **DESCRIPTION AND USES**

Industrial Choice<sup>®</sup> 1600 System Sprays are fast-dry, multipurpose, modified alkyd enamel aerosols for everyday indoor/outdoor industrial applications. These aerosols will spray in any position. Not for use on galvanized steel.

Galvanizing aerosols are used for touch-up and repair to damaged galvanized steel. Do not topcoat with an alkyd finish.

Industrial Choice 1600 System Sprays comply with USDA FSIS regulatory sanitation performance standards for food establishment facilities.

### PRODUCTS

### **PRIMERS**

**CKII** 

SKU	DESCRIPTION
257400	Black Primer
1667830	Red Primer
1680830	Gray Primer
1680830V	Gray Primer
1681830	White Primer
1681830V	White Primer

### **ENAMELS (Flat, Semi-Gloss, & Gloss Finishes)**

DESCRIPTION

SKU	DESCRIPTION
202211	Machine Green
202214	Machinery Gray
202216	Dusty Pink
214644	Electric Green
214645	ANSI 61 Light Gray
214646	ANSI 49 Medium Light Gray
214647	ANSI 70 Light Gray
257399	Purple
257401	Emerald Green
257401V	Emerald Green
257402	Semi-Gloss White
257402V	Semi-Gloss White
273878	Waste Management Green
1610830	Crystal Clear
1614830	Dull Aluminum
1622830	Regal Blue
1622830V	Regal Blue
1624830	OSHA Safety Blue
1626830	True Blue
1626830V	True Blue
1633830	OSHA Safety Green
1638830	Hunter Green
1643830	School Bus Yellow
1644830	OSHA Safety Yellow
1653830	OSHA Safety Orange
1653830V	OSHA Safety Orange

# PRODUCTS (cont.)

ENAMELS (Flat, Semi-Gloss, & Gloss Finishes) cont.

SKU	DESCRIPTION
1660830	OSHA Safety Red
1664830	Cherry Red
1664830V	Cherry Red
1666830	Banner Red
1670830	OSHA Safety Purple
1671830	Beige
1672830	Almond
1674830	Leather Brown
1676830	Ultra-Flat Black
1676830V	Ultra-Flat Black
1678830	Semi-Flat Black
1679830	Gloss Black
1679830V	Gloss Black
1684830	Dove Gray
1686830	Universal Gray
1686830V	Universal Gray
1688830	Smoke Gray
1690830	Flat White
1690830V	Flat White
1692830	Gloss White
1692830V	Gloss White
1696830	Antique White

### **FLUORESCENTS**

SKU	DESCRIPTION	
1632830	Fluorescent Green	
1642830	Fluorescent Yellow	
1654830	Fluorescent Orange	
1655830	Fluorescent Red-Orange	
1659830	Fluorescent Pink	

### **GALVANIZING**

SKU	DESCRIPTION
1685830	Cold Galvanizing Compound
244305	Bright Galvanizing Compound

### **PACKAGING**

1

6 aerosols (16 fl. oz. container, 12 oz. weight fill) per carton. Galvanizing aerosols: 6 aerosols (16 fl. oz. container, 14 oz. weight fill) per carton. 242657: 6 aerosols (16 fl. oz. container, 11 oz. weight fill) per carton.

Form: GD

Form: GDH-11 Rev.: 031122 •TRUSTED QUALITY SINCE 1921•

# **RUST-OLEUM**°

INDUSTRIAL — CHOICE.—

# 1600 SYSTEM MULTI-PURPOSE ENAMELS

### PRODUCT APPLICATION

### **SURFACE PREPARATION**

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with Krud Kutter® Original Cleaner Degreaser, commercial detergent or other suitable cleaner. Rinse immediately and thoroughly and allow to fully dry. Thoroughly cured, hard or gloss previous coatings which are very smooth may require scuff sanding to maximize adhesion. This coating may not be compatible with some types of plastics. It is strongly suggested a small test patch be done before applying to any plastic. Also, some plastics, like polycarbonate, are never to be painted. Consult with the manufacture.

STEEL: Hand tool (SSPC-SP-2) or power tool (SSPC-SP-3) clean to remove loose rust, mill scale, and deteriorated previous coatings. For best results, use Red Primer on sound rusted or clean metal before the application of a finish coat or intermediate primer.

GALVANIZED STEEL: New galvanized steel may contain a surface wax or oil from the fabricator. This must be removed with Krud Kutter Original Cleaner Degreaser, commercial detergent or other suitable cleaner.

**NOTE:** Only the Galvanizing Compounds are to be used on galvanized steel. Do not use any other of the 1600 System Primers or Finish Colors.

WEATHERED GALVANIZED STEEL: Remove loose rust and stains by hand tool (SSPC-SP-2) or power tool (SSPC-SP-3) prior to application of the Cold Galvanizing Compound.

## PRODUCT APPLICATION (cont.)

### **APPLICATION**

Use when temperature is above 50°F (10°C) and humidity is below 85% to ensure proper drying. Surface temperature must be between 50-100°F (10-38°C). Use a primer on bare or rusted surfaces. Protect surrounding surfaces from overspray. Overspray can carry a significant distance. Shake can for one minute after mixing ball is heard. Hold can 10-14" from surface. Apply several light coats a few minutes apart to avoid drips and runs. This aerosol will spray in any position or angle, including upside down.

### **CLEAN-UP**

Wipe off tip before storing. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in trash compactor. Empty container can be recycled.

#### **CLOGGING**

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

Form: GDH-11 Rev.: 031122 •TRUSTED QUALITY SINCE 1921•

## RUST-OLEUM® INDUSTRIAL — CHOICE.—

# 1600 SYSTEM MULTI-PURPOSE ENAMELS

### PHYSICAL PROPERTIES

		FLAT ENAMELS & PRIMERS	GLOSS FINISHES	GALVANIZING*
Resin Type		Modified Alkyd	Modified Alkyd	Epoxy Ester
Pigment Type		Varies with color	Varies with color	1685830 contains 93% zinc in the dry film 244305 contains greater than 65% zinc in the dry film (also contains aluminum)
Solvents		Acetone, xylene, toluene (fluorescents contain hexane) and liquefied petroleum gas propellant		
MIR		Maximum value of 0.70	Finishes: Max. value of .95 Metallics: Max. value of 1.25	Maximum value of 1.25
Fill Weight		12 oz.	Finishes: 12 oz. Metallics: 11 oz.	14 oz.
Recommended Dry Film Thickness Per Coat		1-2 mils (25-50µ)	1-2 mils (25-50µ)	1-2 mils (25-50µ)
Practical Coverage at Recommended DFT <sup>†</sup>		12-15 sq. ft./can (1.1-1.4 m²/can)	12-15 sq. ft./can (1.1-1.4 m²/can)	12-15 sq. ft./can (1.1-1.4 m²/can)
	Touch	10 minutes	10 minutes	10-20 minutes
Dry Times at 70-80°F (21-27°C) and 50%	Handle	1 hour	1 hour	1-2 hours
Relative Humidity	Recoat	Within 1 hour or after 24 hours	Within 1 hour or after 24 hours	Within 1 hour or after 24 hours
Dry Heat Resistance		200°F (93°C)**	200°F (93°C)**	200°F (93°C)**
Shelf Life		5 years	5 years	5 years
Safety Information		For additional information, see SDS		

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Phone: 877-385-8155 www.rustoleum.com/industrial Form: GDH-11 Rev.: 031122

<sup>\*</sup>Do not topcoat galvanizing compounds with an alkyd finish.

<sup>\*\*</sup>Some discoloration may occur at temperatures above 150°F (65°C).

<sup>&</sup>lt;sup>†</sup>Actual coverage with complete hiding. Coverage may vary with color and substrate. The coverage rate can be optimized if applied over the white or gray primer.