



STYCAST 2651-40/Catalyst 9

June 2011

PRODUCT DESCRIPTION

STYCAST 2651-40/Catalyst 9 provides the following product characteristics:

Technology	Epoxy
Appearance (Resin)	Black
Product Benefits	<ul style="list-style-type: none"> • Two component • Ease of use • Low viscosity
Mix Ratio by weight - Material: Catalyst	100 / 8 to 9
Cure	Room temperature and Heat cure
Application	Encapsulant

STYCAST 2651-40/Catalyst 9 epoxy encapsulant is designed to have excellent adhesion to metals, plastics and ceramics. When fully cured, the material is readily machined with carbide tools.

STYCAST 2651-40 can be used with a variety of catalysts. For more information on mixed properties when used with other available catalysts, please contact your local technical service representative for assistance and recommendations.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties 2651-40

Viscosity @ 25 °C,	30
Density , g/cm ³	1.5
Shelf Life @ 18 to 25°C, months	12
Flash Point - See MSDS	

Viscosity will decrease by elevation of temperature to 40°C.

Mixed Properties

Mixed Viscosity @ 25 °C, mPa·s (cP)	5,000
Mixed Pot Life , minutes	30
Flash Point - See MSDS	

TYPICAL CURING PERFORMANCE

For Castings up to 50 grams

1 hour @ 65°C

Cure time and temperature depend on mass and will vary due to other considerations.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

DIRECTIONS FOR USE

1. Mix the resin in the can in which it is received until uniform to texture. This will normally require 2 to 5 minutes in 1 to 5 gallon containers.
2. Blend thoroughly.
3. Pour into mold or container. If necessary, trapped air is readily removed by vacuum evacuation..
4. Allow to stand at room temperature for 8 hours for handling or demolding. Full properties develop over the following 24 hours.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 18 to 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation and its affiliates ("Henkel") specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel products. Henkel specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

All trademarks in this document are trademarks and/or registered trademarks of Henkel in the US and elsewhere.

Reference 0.0



Authorized Distributor

1-800-375-0605

www.rudolphbros.com