



Technical Data Sheet

LOCTITE ABLESTIK 45

June 2021

PRODUCT DESCRIPTION

LOCTITE ABLESTIK 45 provides the following product characteristics:

Technology	Epoxy
Appearance, Resin (Component A)	Black
Appearance, Hardener (Component B)	Black
Components	Two components - requires mixing
Cure	Room Temperature or Heat Cure
Product Benefits	<ul style="list-style-type: none"> • General purpose • Easy mix ratio • Extremely flexible • Variable flexibility • Room temperature cure • Fast cure • Excellent shock and peel resistance
Mix Ratio, by weight - Resin : Hardener	100 : 50
Rigid Formula	
Mix Ratio, by weight - Resin : Hardener	100 : 100
Semi-rigid Formula	
Mix Ratio, by weight - Resin : Hardener	100 : 150
Flexible Formula	
Application	Assembly
Operating Temperature - Rigid	-40 to 90°C
Operating Temperature - Semi-rigid	-55 to 80°C
Operating Temperature - Flexible	-55 to 65°C
Surfaces	Metals, Glass, Ceramics and Plastics

LOCTITE ABLESTIK 45 is designed as a general purpose, adhesive and is particularly useful when bonding dissimilar substrates such as metal to plastic. It is designed for use where shock and peel resistance are desired.

LOCTITE ABLESTIK 45 can be used with a variety of catalysts. For more information on mixed properties when used with other available catalysts, please contact your local technical service representative for assistance and recommendations.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties *ABLESTIK 45*

Viscosity @ 25 °C, mPa·s (cP)	225,000
Specific Gravity	1.58
Shelf Life @ 18 to 25°C, days	270
Flash Point - See SDS	

Part B Properties *LOCTITE CAT 15*

Viscosity @ 25 °C, mPa·s (cP)	25,000
Specific Gravity	0.97
Flash Point - See SDS	

Mixed Properties

Rigid Formulation:

Mixed Viscosity @ 25°C, mPa·s (cP)	37,000
Specific Gravity	1.34
Working Time, 100g mass @ 25°C, minutes	120
Shelf Life @ 25°C, months	6
Flash Point - See SDS	

Semi-Rigid Formulation:

Mixed Viscosity @ 25°C, mPa·s (cP)	37,000
Specific Gravity	1.24
Working Time, 100g mass @ 25°C, minutes	140
Shelf Life @ 25°C, months	6
Flash Point - See SDS	

Flexible Formulation:

Mixed Viscosity @ 25°C, mPa·s (cP)	36,000
Specific Gravity	1.18
Working Time, 100g mass @ 25°C, minutes	160
Shelf Life @ 25°C, months	6
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE AS MIXED

Cure Schedule

16 to 24 hours @ 25°C
4 to 6 hours @ 45°C
2 to 4 hours @ 65°C
15 to 30 minutes @ 105°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.



TYPICAL PROPERTIES OF CURED MATERIAL AS MIXED**Rigid Formulation****Physical Properties**

Coefficient of Thermal Expansion, ASTM D 3386:	
Below Tg, ppm/°C	58
Above Tg, ppm/°C	158
Glass Transition Temperature, ISO 11357-2, °C	48
Thermal Conductivity, W/(m-K)	0.35
Shore Hardness, ISO 868, Durometer D	80
Water Absorption, ASTM D 570, %:	
24 hours	0.2

Electrical Properties

Dielectric Breakdown Strength IEC 60243-1, 14 kV/mm	
Dielectric Constant / Dissipation Factor, IEC 60250:	
60Hz	4.4 / 0.04
1 kHz	4.1 / 0.04
1 MHz	3.4 / 0.03
Volume Resistivity, IEC 60093, Ω·cm	>1×10 ¹³

Semi-rigid Formulation**Physical Properties**

Coefficient of Thermal Expansion, ASTM D 3386:	
Below Tg, ppm/°C	73
Above Tg, ppm/°C	173
Glass Transition Temperature, ISO 11357-2, °C	23
Thermal Conductivity, W/(m-K)	0.35
Shore Hardness, ISO 868, Durometer D	60 to 70
Water Absorption, ASTM D 570, %:	
24 hours	0.5
Tensile Strength, ISO 527-2	N/mm ² 30 (psi) (4,350)
Tensile Modulus, ISO 527-2	N/mm ² 500 (psi) (72,500)
Flexural strength, ASTM D790	N/mm ² 34 (psi) (4,930)
Impact Strength, ASTM-D-256, J/cm	22

Electrical Properties

Dielectric Breakdown Strength IEC 60243-1, 14 kV/mm	
Dielectric Constant / Dissipation Factor, IEC 60250:	
1 MHz	3.3 / 0.08
Volume Resistivity, IEC 60093,	>1×10 ¹³

Flexible Formulation**Physical Properties**

Coefficient of Thermal Expansion, ASTM D 3386:	
Below Tg, ppm/°C	87
Above Tg, ppm/°C	209
Glass Transition Temperature, ISO 11357-2, °C	11
Thermal Conductivity, W/(m-K)	0.35
Shore Hardness, ISO 868, Durometer A	60

Electrical Properties

Dielectric Breakdown Strength IEC 60243-1, 14 kV/mm	
Volume Resistivity, IEC 60093, Ω·cm	>1×10 ¹⁰

TYPICAL PERFORMANCE OF CURED MATERIAL AS MIXED**Rigid Formulation****Lap Shear Strength, ISO 4587:****Aluminum:**

Tested @ 25 °C	N/mm ² 17 (psi) (2,500)
Tested @ 65 °C	N/mm ² 10 (psi) (1,400)

Semi-Rigid Formulation**Lap Shear Strength, ISO 4587:****Aluminum:**

Tested @ 25 °C	N/mm ² 13 (psi) (1,900)
----------------	---------------------------------------

Flexible Formulation**Lap Shear Strength, ISO 4587:****Aluminum:**

Tested @ 25 °C	N/mm ² 4 (psi) (600)
----------------	------------------------------------

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 18 to 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local Henkel representative for assistance and recommendations on the specifications of this product.

Conversions

(°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 N x 0.225 = lb/F
 N/mm x 5.71 = lb/in
 psi x 145 = N/mm²
 MPa = N/mm²
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.



**RUDOLPH
BROS. & CO**



1-800-375-0605
Option 8 for 24/7 Service



www.rudolphbros.com
rbcsupport@rudbro.com

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.5



**RUDOLPH
BROS. & CO**



1-800-375-0605
Option 8 for 24/7 Service



www.rudolphbros.com
rbcsupport@rudbro.com