



productinformation

tesa® 4970

Double-sided filmic tape with high adhesion

tesa® 4970 is a 8.9 mils white double-sided self-adhesive tape consisting of a PVC-film backing and a tackified acrylic adhesive. The product is easily identifiable by its white colour and the mustard yellow liner.

tesa® 4970 features:

- Excellent combination of high tack and immediate adhesion
- High coating weight for good bonding performance on rough or dusty surfaces
- Ideal for longterm bonding applications
- Suitable for mounting and bonding applications in virtually every industry

Main Application

- Mounting plastic and wooden trims
- Mounting decorative point of sale materials and displays
- Mounting signs and scales
- Mounting and bonding in every industry

Technical Data

▪ Backing material	PVC film	▪ Tensile strength	38 N/cm
▪ Color	white	▪ Type of liner	21.7 lbs/in
▪ Total thickness	225 µm	▪ Color of liner	glassine
	8.9 mils	▪ Thickness of liner	brown
▪ Type of adhesive	tackified acrylic	▪ Weight of liner	71 µm
▪ Elongation at break	20 %		2.8 mils
			82 g/m ²

For latest information on this product please visit <http://l.tesa.com/?ip=04970>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

tesa® 4970

Double-sided filmic tape with high adhesion

Adhesion to

▪ Steel (initial)	13.0 N/cm 118.8 oz/in	▪ Steel (after 14 days)	13.6 N/cm 124.3 oz/in
▪ ABS (initial)	13.4 N/cm 122.4 oz/in	▪ ABS (after 14 days)	14.4 N/cm 131.6 oz/in
▪ Aluminium (initial)	11.5 N/cm 105.1 oz/in	▪ aluminium (after 14 days)	12.6 N/cm 115.1 oz/in
▪ PC (initial)	16.2 N/cm 148 oz/in	▪ PC (after 14 days)	16.9 N/cm 154.4 oz/in
▪ PE (initial)	8.5 N/cm 77.7 oz/in	▪ PE (after 14 days)	9.1 N/cm 83.1 oz/in
▪ PET (initial)	11.5 N/cm 105.1 oz/in	▪ PET (after 14 days)	11.9 N/cm 108.7 oz/in
▪ PP (initial)	9.7 N/cm 88.6 oz/in	▪ PP (after 14 days)	10.8 N/cm 98.7 oz/in
▪ PS (initial)	14.7 N/cm 134.3 oz/in	▪ PS (after 14 days)	15.2 N/cm 138.9 oz/in
▪ PVC (initial)	12.4 N/cm 113.3 oz/in	▪ PVC (after 14 days)	16.6 N/cm 151.7 oz/in

Properties

▪ Temperature resistance short term	70 °C 158 °F	▪ Resistance to chemicals	● ● ●
▪ Temperature resistance long term	60 °C 140 °F	▪ Softener resistance	● ● ●
▪ Tack	● ● ●	▪ Static shear resistance at 73,4 °F	● ● ●
▪ Ageing resistance (UV)	● ● ● ●	▪ Static shear resistance at 104 °F	● ●
▪ Humidity resistance	● ● ● ●		

Evaluation across relevant tesa® assortment: ● ● ● ● very good ● ● ● good ● ● medium ● low

Additional Information

A fingerlift version (extended liner), tesa® 7149, is also available.

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



1-800-375-0605
Option 8 for 24/7 Service



6550 Oley Speaks Way
Canal Winchester, OH 43110



www.rudolphbros.com
rbcsupport@rudbro.com