

BONDERITE C-AK 53 AERO**ALKALINE CLEANER**

(KNOWN AS TURCO RIDOLINE 53)

Authorized Distributor



1-800-375-0605 www.rudolphbros.com



Issued 7/31/2014

INTRODUCTION

BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53) is a powdered, silicated, alkaline immersion cleaner for cleaning aluminum, zinc, cadmium or copper surfaces. BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53) is non-etching, non-smutting and free-rinsing at the recommended concentrations and temperatures.

OPERATING SUMMARY

Chemical		Bath Preparation per 100 Gallons
BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53)		6.25 to 18.75 pounds
Operating and Control		
Free Alkali	5.0 to 15.0 points	
Time	1 to 5 minutes	
Temperature	140° to 160° Fahrenheit	
Typical Operation	12.5 pounds per 100 gallons of solution volume, for 3 minutes at 150° Fahrenheit.	

MATERIALS

BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53)

Testing Reagents and Apparatus

EQUIPMENT

The process tank, housing, pumps and piping for use with this solution may be constructed of mild steel. The heat exchanger plates should be polished 316 stainless steel. If gas fired burner tubes are used, they should be made of schedule 80 mild steel pipe or equivalent. All process circulating pump seals, valve seats, door seals, and other elastomers which come in contact with the working process solution should be Buna-N, PTFE, or FKM. EPDM elastomers should be avoided.

Automatic process control equipment, which promotes consistent quality and controlled costs, is available for automatically controlling this process. Auxiliary equipment, which is engineered and specified for this process, include air operated chemical transfer pumps, chemical metering pumps, reliable level controls, solenoid valve assemblies and bulk storage tanks. CHEMIXERS are available in three sizes for preparing solutions of powdered products which then may be metered into the process at a controlled rate. All chemical pump seals, valve seats and other elastomers which come in contact with the concentrated solution can be Buna-N, PTFE, FKM or CSPE.



BONDERITE C-AK 53 AERO ALKALINE CLEANER

(KNOWN AS TURCO RIDOLINE 53)

TREATING WITH THE BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53 SOLUTION)

Buildup:

Concentration: 6.25 to 18.75 pounds of BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53) per 100 gallons (U.S.) of solution (1 to 3 ounces per gallon).

Fill the tank about two-thirds full with ambient to warm water (not above 120° Fahrenheit). Dissolve the required amount of BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53). Add sufficient water to bring the solution up to the working level, mix thoroughly and heat to the operating temperature.

Operations:

Temperature: 140° to 160° Fahrenheit.

Time: 1 to 5 minutes.

The exact time should be determined for each application, since the nature of the soil, concentration of BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53) and temperature of the solution affect the rate of cleaning.

After the best values for time and temperature have been established, they should be closely maintained. Temperature should be held within $\pm 5^\circ$ Fahrenheit.

Once an effective concentration has been determined, maintain it for purposes of economy and efficient cleaning. When such a concentration no longer produces acceptable cleaning, excessive contamination by grease and soil is indicated and the solution should be discarded.

TESTING AND CONTROL

Never pipet by mouth. Use a pipet filler.

Free Alkali:

Pipet a 10 ml sample into a 150-ml beaker. Add 5 drops of Indicator 3. Titrate with Titrating Solution 20 until one drop discharges the last of the pink. The ml of Titrating Solution 20 used is the free alkali value in points.

Free alkali range: within ± 0.5 points of the value found to give the best results.

To increase value 1.0 point (ml): 1.25 pounds of BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53) per 100 gallons (U.S.) of solution.

If desired, the concentration in ounces per gallon or pounds per 100 gallons may be calculated from the following equations or obtained from the table.

Ounces of BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53) per gallon = $0.20 \times$ points.

Pounds of BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53) per 100 gallons = $1.25 \times$ points.

<u>lb per 100 gal</u>	<u>oz per gal</u>	<u>Points</u>
6.25	1.0	5.0
9.40	1.5	7.5
12.50	2.0	10.0
15.60	2.5	12.5
18.75	3.0	15.0



BONDERITE C-AK 53 AERO ALKALINE CLEANER

(KNOWN AS TURCO RIDOLINE 53)

The cleaner solution strength may be increased or reduced depending upon the type of soil, the time available and the characteristics of the equipment in which it is used.

STORAGE REQUIREMENTS

BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53 is a powdered product and does not require special protection in cold weather. The cleaner may absorb moisture and, therefore, it should be stored in a dry area. Opened containers should be kept closed when not in use.

WASTE DISPOSAL INFORMATION

Applicable regulations covering disposal and discharge of chemicals should be consulted and followed.

Disposal information for the chemical in the form as supplied, is given on the Material Safety Data Sheet for the chemical.

The processing bath is alkaline and contains phosphates. Waste treatment and/or neutralization of rinse water or processing solution may be required prior to discharge. (Refer to Waste Treatment Information Bulletin WT1007, available on request.)

The processing bath and sludge, which accumulates in the bath can contain ingredients other than those present in the chemical as supplied and analysis of the solution and/or sludge may be required prior to disposal.

PRECAUTIONARY INFORMATION

When handling the chemical used in this process, the precautionary, first aid and handling recommendations on the Material Safety Data Sheet for the product must be read, understood and followed.

The processing bath is alkaline and can cause irritation of the skin and may burn eyes. Do not get in eyes, on skin or on clothing. In case of contact, follow the recommendations on the Material Safety Data Sheet for BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53.

**BONDERITE C-AK 53 AERO
ALKALINE CLEANER**

(KNOWN AS TURCO RIDOLINE 53)

Testing Reagents and Apparatus
(Order only those items which are not already on hand.)

<u>Code</u>	<u>Quantity</u>	<u>Item</u>
89000-202**	2*	Beaker, 150-ml
17579-482**	1	Buret Assembly, 25-ml Automatic
592398	1 qt	Indicator 3 (phenolphthalein)
592475	1	Indicator Dropping Bottle
89003-350**	2*	Pipet, 10-ml Volumetric
53497-009**	1	Pipet Filler
30250***	1	Thermometer, Floating
592430	1 gal	Titration Solution 20 (0.1N H ₂ SO ₄)

*Includes one more than actually required, to allow for possible breakage.

**VWR Part # - vwr.com or 800-932-5000

***Thomas Scientific Part #



**BONDERITE C-AK 53 AERO
ALKALINE CLEANER**

(KNOWN AS TURCO RIDOLINE 53)

Company _____ Technical Process Bulletin No. 234242

Plant _____ Unit _____

Henkel Technologies Representative _____

Telephone _____ Sales Office Telephone _____

3

3

3

BONDERITE C-AK 53 AEROTank _____³ Tank No. _____.³ Working Volume _____ gallons.³ _____ gallons per inch.

3

Buildup _____³(Section 5) ³ _____ pounds of BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53).

3

Operation _____³ Time: _____ minutes _____ seconds.(Section 5) ³ Temperature: _____ ° to _____ ° Fahrenheit.

3

Testing and _____³Control _____³(Section 6) ³ **Free Alkali:** Test every _____.³ 10 ml sample,³ add 25 ml water and 5 drops Indicator 3.³ Titrating Solution 20 until one drop discharges the last of³ pink color.

3

³ Range: _____ to _____.³ Add _____ pounds _____ ounces of BONDERITE C-AK 53 AERO (KNOWN AS TURCO RIDOLINE 53³ for _____ point.

3

³

<u>lb per 100 gal</u>	<u>oz per gal</u>	<u>Points</u>
³ 6.25	1.0	5.0
³ 9.40	1.5	7.5
³ 12.50	2.0	10.0
³ 15.60	2.5	12.5
³ 18.75	3.0	15.0

Authorized Distributor

1-800-375-0605 www.rudolphbros.com

Henkel Corporation | 32100 Stephenson Highway | Madison Heights, MI 48071

PHONE: (248) 583-9300 | FAX: (248) 583-2976 | www.henkelna.com/

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.**

The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

