

LOCTITE EA 9820 AERO

Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9820)

INTRODUCTION

LOCTITE EA 9820 AERO is an intermediate density, one-component epoxy syntactic for use on honeycomb composite parts requiring high compressive strength at temperatures up to 350°F (177°C). LOCTITE EA 9820 AERO may also be used for fastener or attachment potting and panel edge reinforcing.

FEATURES

- One Part Structural Syntactic
- High Density
- High Compressive Strength
- Dual Cure System 250°F (121°C) or 350°F (177°C)
- Long Pot Life

Properties

Color	Amber
Cured Density, g/cc	1.12
Work life @ 77°F (25°C), after thaw, hours	>8
Vertical Flow 30 min., inches @ 77°F (25°C) or 125°F (52°C)	<0.1
Shelf Life @ 10°F (-12°C) or below	9 Months

Handling Characteristics

For consistent extrusion rate performance the following handling recommendation should be performed. Remove frozen cartridges from the freezer and allow the cartridges to thaw at 65-90°F (18-32°C) for 4 hours. Place the cartridges in a sealed waterproof plastic bag and place into a controlled water bath set at 77°F (25°C) for 4 hours prior to extrusion. Recommended extrusion process would be to use a pneumatic hand gun at 85 psi (6 bar) without nozzle.

Cure Schedule

Heat the material from room temperature at the rate of 3.0± 1°F (1.7±0.6°C) per minute to either 250°F (121°C) for 90-100 minutes or 350°F (177°C) for 60-70 minutes. Recommend a cool down rate of 3-5°F (1.7-2.8°C) per minute to room temperature.



Authorized Distributor

1-800-375-0605

www.rudolpbros.com



LOCTITE EA 9820 AERO

Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9820)

Typical Cured Properties

Compression Strength Typical Average Performance

- Specimen Dimension: 0.5" thickness x 1" width x 2" height (12.7 mm x 25.4 mm x 50.8 mm)
- Test method per ASTM D695 with a test rate of 0.05 inches per minute (1.27 mm per minute)
- Ten specimens tested per test condition

Cure Schedule	Specimen Conditioning	Test Temp.		2% Offset		Ultimate	
		°F	°C	KSI	MPa	KSI	MPa
250°F (121°C)	None	77	25	17.9	123.4	22.6	155.9
		250	121	8.4	57.9	12.7	87.6
350°F (177°C)	None	77	25	16.6	114.5	22.8	157.2
		350	177	8.4	57.9	12.5	86.2
350°F (177°C)	Heat Aging 500 hours at 350°F (177°C)	77	25	18.0	124.1	25.1	173.1
		350	177	14.0	96.6	15.6	107.6

Handling Precautions

Do not handle or use until the Material Safety Data Sheet has been read and understood.
For industrial use only.

DISPOSAL INFORMATION

Dispose of spent remover and paint residue per local, state and regional regulations. Refer to HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional disposal information.

PRECAUTIONARY INFORMATION

General:

As with most epoxy based systems, use this product with adequate ventilation. Do not get in eyes or on skin. Avoid breathing the vapors. Wash thoroughly with soap and water after handling. Empty containers retain product residue and vapors so obey all precautions when handling empty containers.

PART A

CAUTION! This material may cause eye and skin irritation or allergic dermatitis. It contains epoxy resins.

PART B

WARNING! This material causes eye and skin irritation or allergic dermatitis. It contains amines.

Before using this product refer to container label and HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional precautionary, handling and first aid information.



LOCTITE EA 9820 AERO Epoxy Paste Adhesive (KNOWN AS Hysol EA 9820)

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Rev. 7/2013



Authorized Distributor

1-800-375-0605

www.rudolpbros.com

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

