



# TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

## DAP® Concrete Floor Leveler - Dry Mix

### PRODUCT DESCRIPTION

DAP® Concrete Floor Leveler is designed for use with DAP® Bonding Liquid & Floor Leveler Additive\* to provide an underlayment system that levels interior or exterior concrete, masonry and wood subfloors. It can be used to patch concrete and masonry steps, sidewalks and curbs. DAP Concrete Floor Leveler is ideal for patios and garage floors.

\*Please refer to the DAP Bonding Liquid & Floor Leveler Additive Technical Bulletin for further information.



PACKAGING	COLOR	UPC
5 lbs.	Gray	7079810414
25 lbs.	Gray	7079810416

### KEY FEATURES & BENEFITS

- Contained Portland Cement
- Levels rough, uneven floors
- Can be used for patching

### SUGGESTED USES

For leveling concrete, masonry, and wood subfloors.



# TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

## KEY FEATURES & BENEFITS

### Surface Preparation & Application

1. Surface must be structurally sound, clean, and free of dust, dirt, paint, soap film, oil, adhesive, grease, chemical concrete curing compounds, and other foreign material.
2. Clean surfaces with damp mop and nail any loose wood flooring prior to application.
3. In a clean container add DAP Concrete Floor Leveler to DAP Bonding Liquid & Floor Leveler Additive in specified ratio. Do not mix more materials than can be used in 45 minutes.
4. Do not use mixture after it has begun to set.
5. Apply a skim coat of the mixture to fill all broken areas, depressions, and cracks in surface of substrate, level and smooth to a feather edge with a gauged spreader or trowel.
6. For repairs greater than 1/2 inch in thickness, apply two equal 1/4" layers, allowing the first layer to dry before applying the second. Do not over trowel. Do not use for repairs exceeding 1 inch in total thickness.
7. If painting is desired, always use a high-quality, latex-based or masonry paint rated for traffic application. Paint may only be applied to a fully cured DAP Concrete Floor Leveler (28 days).

### Mixing Ratios and Coverage:

#### Dry Floor Leveler

5 lb.  
25 lb.

#### Bonding Liquid

1 Pint  
2.5 Quarts

#### Coverage at 1/8" Thickness

5 Square Feet  
25 Square Feet

## TYPICAL PHYSICAL & CHEMICAL PROPERTIES

Working Time:	45 minutes
Setting Time:	3 to 4 hours (allow at least 24 hours of curing prior to installing floor covering)
Final Cure:	28 days
Freezing:	Additive stable 5 cycles at 0°F
Application Temperature:	+40°F
Clean-up:	With water immediately after use
Shelf Life:	12 months



# TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

## CLEAN UP & STORAGE

Wash tools immediately after use with water before product has set. Dried material must be mechanically scraped, chipped or ground away. Close container tightly and store any remaining powder in a cool, dry place.

## SAFETY

See product label and Safety Data Sheet (SDS) for health and safety information. You can request an SDS by visiting our website at [dap.com](http://dap.com) or by calling **888-DAP-TIPS**.

## WARRANTY

### **Limited Warranty:**

If product fails to perform when used as directed, within one year of date of purchase, call 888-DAP-TIPS, with your sales receipt and product container available, for replacement product or sales price refund. DAP Products, Inc. will not be responsible for incidental or consequential damages.

## COMPANY IDENTIFICATION

**Manufacturer:** DAP Products Inc., 2400 Boston Street, Baltimore, Maryland 21224

**Usage Information:** Call **888-DAP-TIPS** or visit [dap.com](http://dap.com) & click on "Ask the Expert"

**Order Information:** 800-327-3339 or [orders@dap.com](mailto:orders@dap.com)

**Fax Number:** 410-558-1068

**Also, visit the DAP website at [dap.com](http://dap.com)**