

Type of Adhesive: Hot Melt Adhesive

Field of Application: Labeling > Roll or Magazine Fed Labelers

Typical Technical Data:

Viscosity: 600 to 1000 cPs at 300°F

Color: Light Yellow

Ring & Ball Softening Point: 155°F

Application Temperature: 250°F to 325°F

Properties:

TECHNOMELT EM 377 is a high performance, low viscosity, pressure sensitive labeling hot melt designed to run on roll or magazine fed labelers. It features aggressive tack, which patterns well with little adhesive applied. It has excellent flexibility and outstanding machining properties, while maintaining strength and adhesion. All ingredients in TECHNOMELT EM 377 are approved under the Federal Regulation 21 CFR 175.105, which relates to incidental contact of adhesives with food.

Handling and Application:

To avoid accidental contamination, keep container covered as soon as sufficient hot melt has been removed for use.

Precautions:

No health hazards are expected with this product in its solid form. Once melted, it is like any hot liquid in that it can produce severe burns. Care should be taken to avoid getting the hot liquid adhesive on the skin. If this occurs, flush the affected area with large amounts of cold water. Do not try to remove the solidified hot melt. Seek Medical Attention immediately. Please refer to the Material Safety Data Sheet for further information.

Storage Conditions:

Do not Store in high temperatures.

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all marks used are trademarks of Henkel or its affiliates in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Distributed by:
Rudolph Bros. & Co.
6550 Oley Speaks Way
Canal Winchester, OH 43110
Phone: 614-833-0707
Fax: 800-600-9508
e-mail: rbcsupport@rudbro.com
www.rudbro.com