



Technical Data Sheet

# LOCTITE ABLESTIK SF 40

June 2016

## PRODUCT DESCRIPTION

LOCTITE ABLESTIK SF 40 provides the following product characteristics:

<b>Technology (Part A)</b>	Epoxy
<b>Technology (Part B)</b>	Amine
Appearance - Part A	White paste
Appearance - Part B	Amber liquid
Product Benefits	<ul style="list-style-type: none"> <li>• Two component</li> <li>• Lightweight</li> <li>• Non-sag</li> <li>• Room temperature cure</li> <li>• Thixotropic</li> <li>• Low density syntactic foam</li> <li>• Good bond strength</li> <li>• Machinable</li> </ul>
Components	Two components - requires mixing
Mix Ratio, by weight - Part A: Part B	100 : 9
<b>Cure</b>	Room Temperature or Heat Cure
<b>Application</b>	Non-conductive adhesive
Typical Assembly Applications	Aerospace applications and Hydrospace applications
Key Substrates	Ceramics, Metals and Plastics
Operating Temperature Range	-40 to 120°C

LOCTITE ABLESTIK SF 40 is a good choice for repairing vertical surfaces with little added weight.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

### Part A Properties ECCOBOND SF 40

Density, ASTM D792, g/cm <sup>3</sup>	0.61
---------------------------------------	------

### Part B Properties ECCOBOND SF 40

Brookfield Viscosity, ASTM D2393, mPa·s (cP)	95
Density, ASTM D792, g/cm <sup>3</sup>	0.98

### Mixed Properties

Density, ASTM D792, g/cm <sup>3</sup>	0.64
Work Life (100 g) @ 25 °C, minutes	30
Shelf Life @ 25°C, days	365
Flash Point - See SDS	

## TYPICAL CURING PERFORMANCE

### Cure Schedule

48 to 72 hours @ 25°C or  
2 to 4 hours @ 65°C

For optimum performance, follow the initial cure with a post cure of 2 to 4 hours at maximum expected operating temperature.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties

Hardness, Shore D, ASTM D2240	70
Water Absorption, ASTM D 570, %	2.0
Coefficient of Thermal Expansion, ASTM D3386:	
Below Tg, ppm/°C	33
Above Tg, ppm/°C	107
Glass Transition Temperature, ASTM D3418, °C	107

### Electrical Properties

Dielectric Strength, ASTM D149, kV/mm	13.8
Dielectric Constant / Dissipation Factor, ASTM D150:	
@ 1mHz	2.5/0.02
Volume Resistivity @ 25 °C, ASTM D257, ohm-cm	1×10 <sup>12</sup>

### Outgassing Properties

Outgassing, ASTM E 595, %:	
TML	0.23
CVCm	0.04

## TYPICAL PERFORMANCE OF CURED MATERIAL

### Miscellaneous

Tensile Lap Shear Strength :

Al to Al:	
@ 25 °C	N/mm <sup>2</sup> 14.5 (psi) (2,100)
@ 65 °C	N/mm <sup>2</sup> 12.4 (psi) (1,800)

## GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

## DIRECTIONS FOR USE

1. Complete cleaning of the substrates should be performed to remove contamination such as oxide layers, dust, moisture, salt and oils which can cause poor adhesion or corrosion in a bonded part.
2. Some filler settling is common during shipping and storage. For this reason, it is recommended that the contents of the shipping container be thoroughly mixed prior to use. Power mixing is preferred to ensure a homogeneous product.
3. Accurately weigh resin and hardener into a clean container in the recommended ratio. Weighing apparatus having an accuracy in proportion to the amounts being weighed should be used.
4. Blend components by hand, using a kneading motion, for 2 to 3 minutes and scrape the bottom and sides of the mixing container



frequently to produce a uniform mixture.

5. If possible, power mix for an additional 2 to 3 minutes. Avoid high mixing speeds. This can entrap excessive amounts of air. It can also cause overheating of the mixture, resulting in reduced working life.
6. Apply adhesive to all surfaces to be bonded and join together.
7. In most applications only contact pressure is required.
8. Certain resins and hardeners are prone to crystallization. If crystallization does occur, warm the contents of the shipping container to 50 to 60°C until all crystals have dissolved. Shipping container must be loosely covered during the warming stage to prevent any pressure build-up.

#### Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

#### Storage

Store in original, tightly covered containers in clean, dry areas. Storage information may be indicated on the product container labeling.

#### Optimal Storage : 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

#### Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{psi} \times 145 = \text{N/mm}^2$   
 $\text{MPa} = \text{N/mm}^2$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

#### Disclaimer

##### Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is,

therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.


**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

#### Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1



1-800-375-0605  
Option 8 for 24/7 Service



6550 Oley Speaks Way  
Canal Winchester, OH 43110



www.rudolphbros.com  
rbcsupport@rudbro.com