

F565-4010 Intermediate Coating (US)


TECHNICAL DATA SHEET

Product Description

F565-4010 product is a polyamide-based coating used as an intermediate coat in the selectively strippable exterior paint systems. It is applied directly over the corrosion resistant primer (chromated or non-chromated) and is then top coated with Desothane® HS or HD topcoats.

- Easily removed with mild strippers such as PR-3135
- Decreases stripping time
- Excellent fluid resistance
- Compatible with all current spray equipment
- Can be applied in a wide range of conditions
- Service temperature -54°C to 177°C (-65°F to 350°F)

Components



Mix ratio (by volume):

- F565-4010 (base component) 4 parts
- F275-0189 (activator component) 1 part
- 020K026 or 020K026R (thinner component) 2 parts

Specifications



F565-4010 coating is qualified to:

- AFS1821
- BMS 10-120 Type I Grade A

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

Product Compatibility:

F565-4010 coating is compatible with the following topcoat specifications:

- BAMS 565-009
- BMS 10-60 Type I & Type II
- BMS 10-72 Type VIII
- BMS 10-125 Type III
- CMS-CT-101
- DMS 2115
- DPM 2143
- MEP 10-069
- MIL-PRF-85285
- MM1276

F565-4010 coating is compatible with the following primer specifications:

- BAMS 565-008
- BMS 10-72 Type VIII
- BMS 10-79 Type II & Type III
- BMS 10-118 Type I
- CMS-CT-201
- DHMS 04.18
- DMS 2104
- DPM 2144
- MEP 10-068
- MM1275

F565-4010 Intermediate Coating (US)

Surface Preparation and Pretreatments



F565-4010 coating can be applied over clean, dry, intact primed surfaces. For further information, refer to the Technical Data Sheet for the above mentioned primers.

Instructions for Use



Mixing Instructions:

Prior to mixing, thoroughly shake the F565-4010 base. Add F275-0189 activator to the base component under agitation. Then add 020K026 or 020K026R thinner while stirring. Maintain constant agitation for 10 minutes to ensure proper mixing.

Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 13° and 35°C (55° to 95°F). The minimum temperature of the paint components should be 13°C (55°F) prior to mixing.



Induction Time:


Not Required



Viscosity: (23°C/73°F)

- | | |
|-------------------------|------------------|
| • #2 Signature Zahn cup | 12 to 16 seconds |
| • #4 Ford cup | 10 to 12 seconds |
| • ISO 3mm cup | 30 to 37 seconds |
| • ISO 4mm cup | 16 to 18 seconds |
| • BSB3 cup | 23 to 26 seconds |
| • BSB4 cup | 13 to 15 seconds |
| • AFNOR #2.5 cup | 40 to 45 seconds |
| • AFNOR #4 cup | 13 to 15 seconds |

Note: Viscosities quoted are the typical ranges obtained when using specified mix ratio.



Pot Life:

8 hours @ 21 - 25°C (70 - 77°F)

F565-4010 Intermediate Coating (US)

Application Guidelines

Recommended Application Conditions:

Temperature	15 - 30°C (59 - 86°F)
Relative Humidity	20 - 90%

Application:


Ground the aircraft and the application equipment before coating. Stir the intermediate coating slowly during the application. The suggested film thickness is 8 to 12 microns (0.3 to 0.5 mils). This can be accomplished by one medium cross coat with a 50% overlap. Note the spray equipment must be flushed with Isopropyl alcohol before using the intermediate coating. Small amounts of strong solvents such as MEK are not compatible with the intermediate coating.

These application guidelines represent PPG's best advice in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.



Theoretical Coverage:

10 square meters/liter at 25 microns dry film (400 square feet/gallon at 1 mil dry film)
 Recommended dry film thickness; 8 to 12 microns (0.3 to 0.5 mils)



Dry Film Density:

1.48 grams/cubic centimeter (12.33 pounds/gallon)

Dry Film Weight:

37 grams/square meter at 25 microns dry film (0.0078 pounds/square feet at 1 mil dry film)

F565-4010 Intermediate Coating (US)



Equipment:

F565-4010 is compatible with the following spray equipment. When using with electrostatic equipment ensure that the E-Stats is set to off.

Equipment Type	Tip Size	Pot Pressure	Atomization Pressure at the Cap
Air Spray Gun	1.2 mm or 1.5 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)
Air Assisted Airless Spray Gun	#611 or #613 (Graco Nomenclature)	700 to 1200 psi (48 to 82 bar)	40 to 60 psi (2.8 to 4.1 bar)
High Volume Low Pressure Spray Gun (HVLP)	1.0 mm to 1.4 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.2 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

Equipment Cleaning:

Clean spray equipment as soon as possible after use. Flush spray equipment first with Isopropyl Alcohol and then with DeSoto® CN20, DeSoto® CN44, or Desoclean™ 45 high performance solvent cleaner.

Physical Properties (product)



Color: Light Grey



Gloss: Not Applicable



Dry Times	13 - 21°C (55 - 70°F)	22 - 28°C (71 - 84°F)	>29°C (>85°F)
Dust Free	20 minutes	15 minutes	12 minutes
Dry to Tape	3 - 4 hours	2 - 3 hours	1 ½ - 2 hours
Dry Topcoat	3 - 10 hours	2 - 10 hours	1 - 10 hours
Dry Hard	10 hours	8 hours	7 hours
Full Cure	7 days	7 days	7 days

F565-4010 Intermediate Coating (US)

Accelerated cure:

Allow 30 minutes flash off at 24°C ± 3°C (75°F ± 10°F)
followed by 30 minutes at 49°C (120°F) for dry to topcoat

VOC

VOC:

Mixed, ready to use VOC (EPA method 24)	750 grams/liter
Base Component	696 grams/liter
Activator Component	806 grams/liter
020K026 or 020K026R	800 grams/liter



Flash point closed cup:

Base Component	23°C (73°F)
Activator Component	23°C (73°F)
020K026	12°C (53°F)
020K026R	12°C (53°F)

Shelf Life:


12 months from date of manufacture to most OEM material specifications. Consult the specification to verify shelf life requirements.

24 months from date of manufacture for PRC-DeSoto Standard.

Note: Shelf life is provided for original, unopened containers.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.



F565-4010 Intermediate Coating (US)

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC – South Europe

Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

Desoclean, Desothane, and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG-DeSoto International, Inc.

12780 San Fernando Road
Sylmar, CA 91342

www.ppgaerospace.com

Issue Date: 9/15
Lit: 4183