



Authorized Distributor  
1-800-375-0605  
www.rudolphbros.com



# Product Datasheet

## Urethane Elastomer System

# XP2016-047

Version: 101116

**XP2016-047** is a two-component system consisting of Iso (BC809 Iso Part A) and Curative (XP2016-047 Part B). It produces a **90A** polymer and is designed to be used where curing at ambient temperatures and high level of mechanical properties of cured material is desired. The product is MbOCA-free and contains no heavy metal catalysts.

**General Performance Properties:** *Cured 10-days. @ room temperature*

Hardness, Shore A	90 +/- 2	
Ultimate Tensile, psi	2100	ASTM D412
Elongation, %	600	ASTM D412
Tear strength, Die C, pli	400	ASTM D624C
Tear strength, split, pli	100	ASTM D470

**Processing Conditions**

Mix ratio (wt A/wt B), Iso= <b>BC809A</b>	100 : 42
Pot life (100,000 cps viscosity), minutes	20
Demold time , hours	24 @ 25°C (77°F)
Curing time for max properties, days	7 @ 25°C (77°F)

**Iso Side A (BC809A) Properties**

Viscosity, cps (mPa·s) @ 25°C (77°F)	5700
Density, lbs/gallon @ 25°C (77°F)	9.047
Appearance	Colorless to yellow liquid
Storage and use conditions	Keep in a cool, dry place tightly sealed. Pad used containers with dry nitrogen for best storage performance. Avoid elevated use or storage temperatures as this will degrade the NCO content and hurt the final polymer's physical properties.



# Product Datasheet

## Urethane Elastomer System

# XP2016-047

Version: 101116

### Curative Side B Properties

Viscosity, cps (mPa·s) @ 25°C (77°F)	400
Density, lbs/gallon @ 25°C (77°F)	9.050
Appearance	Amber liquid
Shelf Life, months	12
Storage conditions	Keep in a cool, dry place tightly sealed. Pad used containers with dry nitrogen for best storage performance.

**Safety: Read and understand MSDS's before use. Use only in well ventilated areas. Avoid contact with skin. Wear chemical resistant gloves and proper safety equipment. If swallowed, call physician immediately. For eye contact, flush with water for 15 minutes and get medical attention.**

The conditions for your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by BCC Products. All information is given without warranty or guarantee. It is expressly understood and agreed that customer assumes and hereby expressly releases BCC Products from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind BCC Products. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

V.101116

Page 2